



FOR GOOD REASONS

---

# panDOMO<sup>®</sup> SP-MS

## Zīdaini matēts impregnēšanas līdzeklis

---

Plēvi veidojošs, ūdens bāzes impregnēšanas līdzeklis.

- Zīdaini matēts.
- Neslīdošs.
- Izturīgs pret traipiem.
- Nodilumizturīgs.
- Izturīgs pret skrāpējumiem.



Reg.No. 37344

Manufacturer  
with certified quality system  
as per DIN EN ISO 9001

# panDOMO® SP-MS

## Zīdaini matēts impregnēšanas līdzeklis

### Lietošana:

#### Iekštelpās.

Plēvi veidojošs akrila-vaska impregnēšanas līdzeklis uz ūdens bāzes.

PANDOMO SP-GS zīdaini matēts impregnēšanas līdzeklis, noslēdzošās aizsarg kārtas iegūšanai PANDOMO grīdas sistēmām, kas ir ieeļļotas ar PANDOMO SP-SL akmens eļļu vai impregnētas ar PANDOMO SP-PS ūdens poliuretāna impregnēšanas līdzekli.

Ar PANDOMO® SP-SL akmens eļļu apstrādātas grīdas virsmas vispirms jāgruntē ar PANDOMO® SP-F grunti poru aizpildīšanai.

#### Īpašības:

- Ar pretslīdes iedarbību
- Pārklājums nodrošina īslaicīgu aizsardzību pret šķīdriem
- Nodilumizturīgs
- Zīdains finišs

PANDOMO® SP-MS zīdaini matēts impregnēšanas līdzeklis ir netrumus atgrūdošs un pieš ir apstrādāt mēģinājumveidgu, satina finišu.

#### Uzklāšana:

PANDOMO® SP-MS zīdaini matētu impregnēšanas līdzekli drīkst uzklāt tikai uz pilnīgi sausas PANDOMO® SP-F grunts (vismaz 4 stundu žāvēšanas laiks aptuveni + 20 ° C temperatūrā) vai pilnīgi sausām virsmām, kas ir apstrādātas ar PANDOMO® SP-PS. (vismaz 12 stundu žāvēšanas laiks aptuveni + 20 ° C temperatūrā).

PANDOMO® SP-MS uzklāšanai izmantojiet rakeļu (rakeļa tipa), lai izveidotu plānu, vienmērīgu kārtu.

Sākotnējā apstrāde sastāv no 2 uzklāšanas gaidīšanas laiks starp pirmo un otro kārtu būs atkarīgs no žāvēšanas apstākļiem un būs apm. 60 minūtes istabas temperatūrā apm. + 20 ° C un relatīvais mitrums apm. 60%. Uzklāšanas laikā gaisa un zemes temperatūrai jābūt vismaz + 15 ° C.

Neļaujiet sausas virsmas. Izvairieties no apdullināšanas, tūlīt atkal noslaukot virsmu.

#### Notice:

Do not combine PANDOMO® SP-MS Satin-finish Sealer with other maintenance or cleaning products and do not use it for regular maintenance cleaning.

Do not walk on or wipe the floor as long as the protective coat still has a moist sheen.

Clean tools immediately after use with plenty of water.

Fine matting traces may be visible on dark PANDOMO® Floor surfaces after the first application.

Do not apply maximum loads until the stone oil or PU sealer is hard until approx. 5-7 days after initial treatment (depending on climate).

### Maintenance cleaning:

Regular maintenance cleaning can be carried out using PANDOMO® SP-CR Maintenance and Repair Cleaner.

First remove dirt and sand using a broom or the brush side of a vacuum cleaner.

Dilute PANDOMO® SP-CR in the ratio of approx. 50 ml to 8 litres of water.

Wipe surfaces with damp not wet cloth and leave to dry. Do not wipe again with clear water. See Technical Data Sheet for further details.

### Basic cleaning:

To remove stubborn dirt and stains that resist regular maintenance cleaning, we recommend a thorough deep cleaning. Use PANDOMO® SP-BC Basic Cleaner for this purpose. See Technical Data Sheet for details.

After deep-cleaning the floor with PANDOMO® SP-BC, it must be left to dry for a sufficiently long time. The floor must be completely dry before re-applying PANDOMO® SP-SL and PANDOMO® SP-MS. At least two coats of PANDOMO® SP-MS must be applied after a floor has been deep-cleaned.

### General remarks:

The less the newly treated floor is used during the first few days, the longer it will last!

### Notes on safety and waste disposal:

In case of contact with eyes: Rinse with water, including under eyelids.

In case of contact with skin: As a precaution, wash with plenty of water and soap.

If swallowed: Rinse mouth with water and drink plenty of water. Avoid vomiting if possible. If necessary, consult a doctor.

Conditions to be avoided: Do not expose to temperatures above +35°C.

Keep out of the reach of children.

Dispose of contents/containers in accordance with local/regional/national/international regulations.

# panDOMO<sup>®</sup> SP-MS

## Zīdaini matēts impregnēšanas līdzeklis

### Technical data based on ARDEX Quality Standards:

<b>Coverage:</b>	25 ml/m <sup>2</sup> per coat
<b>Density</b>	1.03 g/cm <sup>3</sup>
<b>pH value:</b>	approx. 8.5
<b>Appearance:</b>	cloudy, whitish liquid
<b>Solubility in water:</b>	complete
<b>Working temperature:</b>	+15 – +25°C surface temperature, turn down or switch off floor heating in good time.
<b>Drying time:</b>	Dry to touch after approx. 30 minutes. Can be walked on carefully after approx. 2 hours. Full load-bearing capacity after 3 – 5 days. During this time, surfaces should only be cleaned with dry cloth or clear water. Low temperatures and high humidity will prolong the drying time.

**Labelling according to GHS/CLP:** None

**Labelling according to GGVSEB/ADR:** None

**GISCODE:** GE10

**Packaging:** 5-litre plastic canister

**Storage:** Store in cool but frost-proof surroundings, reseal containers tightly after opening.

**Shelf life:** Can be stored for approx. 12 months in original unopened containers. After opening containers, use up contents as soon as possible.

Mēs uzņemamies garantiju mūsu produktu nevainojamai kvalitātei. Mūsu apstrādes ieteikumi ir balstīti uz izmēģinājumiem un praktisko pieredzi; tos tomēr var uzskatīt tikai par vispārīgiem ieteikumiem bez kvalitātes garantijas, jo mums nav ietekmes uz darba vietas nosacījumiem un darba izpildi. Dažādu valstu noteikumi atkarībā no vietējiem standartiem, būvniecības noteikumiem vai nozares vadlīnijām var ietvert atsevišķas uztādīšanas rekomendācijas.