

Dammbindning 1K / Putekļu saistviela

Hagmans Dammbindning 1K ir bezkrāsaina putekļu saistviela /grunts uz ūdens bāzes. Tā uzlaboto virsmas adhēziju un vēl vairāk nostiprina virsmu. Piemērots lietošanai uz cementa un citām minerālām pamatnēm. Var izmantot gan iekštelpās, gan ārā.

Bāzes materiāls:	Akrila dispersija
Blīvums:	1.01
Materiāla patēriņš:	6-8m ² /l
Žūšanas laiks:	Apmm. 1h (20°C, 50% RH)
Difūzijas īpašības:	Ūdens tvaiku caurlaidoša
Krāsa:	Caurspīdīgs
Iepakojums:	1L, 4L, 10L un 25L
Derīguma termiņš:	2 gadi




SAGATAVOŠANA:

Jaunām cementa virsmām pirms apstrādes ir jācietē vismaz nedēļu, kā arī tām jābūt sausām un brīvām no netīrumiem, eļļām un līdzīga tipa netīrumiem. Cementa izlīdzinošā kārtā jānoņem, ar slīpēšanu vai ar skalošanu ar skābes šķīdumu.

LIETOŠANAS INSTRUKCIJA:

Uzklāt vienā kārtā ar krāsošanas otu, rullīti vai arī ar zemspiediena smidzināšanas pistoli. Pārlicinieties, ka ventilācija ir pietiekama. Ja gaisa mitrums pārsniedz 85%, virsma var būt blāva un plankumaina. Krāsošanas otas un citu aprīkojumu var tīrīt ar ūdens palīdzību. Neveiciet virsmu apstrādi, ja gaisa temperatūra ir zemāka par +5°C.

	
Hagmans Kemi AB Box 112 51110 Fritsla 13	
EN 1504-2 38501-002	
Produkts betona virsmu aizsardzībai Pārklājums	
Reakcija uz uguni Ūdens tvaiku caurlaidība Kapilārā absorbcija un ūdenscaurlaidība Adhēzijas izturība	B _{rr} -s1 Klase I w < 0,1 kg/m ² h ^{0.5} >2,0 N/mm ²

Dustbinder

Hagmans Dammbindning 1K (1-C dust binder) is a colour less, water-borne acrylic-based dust binder/primer for cement and other absorbent mineral substrates.


Hagmans Dammbindning 1K is primarily intended for dust binding in cement floors and walls where it also strengthens the surface. It can also be used as a primer when painting with Golvfärg 1K (1-C floor paint) on clean cement outdoors, such as balconies or stairs, for better adhesion and to further strengthen the surface.

Basic material:	Acrylic dispersion
Density:	1.01
Material consumption:	6-8m ² /l
Drying time:	approx. 1 hour (20°C, 50% RH)
Diffusion properties:	Diffusion opens
Colour:	Transparent
Packaging:	1, 4, 10, and 25 liters
Pot life:	2 years

Preparation: new cement must be cured for a least one week, be dry and free of dirt, oil and similar. The cement skin must be removed, such as by grinding or with an acid wash.

Instructions for use: Apply in a layer with a paintbrush, roller or low pressure spray gun. Make sure ventilation is good. If the humidity levels exceed 85% a matt, streaked surface may result. Paintbrushes and other equipment can be cleaned with water. Do not treat surfaces with a temperature lower than 5°C.



	
Hagmans Kemi AB Box 112 51110 Fritsla	
13	
EN 1504-2	
38501-002	
Product for the protection of concrete surfaces Coating	
Reaction to fire Permeability to water vapour Capillary absorption and permeability to water Adhesion strength	B _{fl} -S1 Class I w < 0,1 kg/m ² h ^{0,5} >2,0 N/mm ²