

Golfvärg 1K / 1K grīdas krāsa

PRODUKTA APRAKSTS:

Golfvärg 1K grīdas krāsa ir nodilumizturīga, viegli lietojama poliuretāna / akrilāta krāsa grīdām un sienām gan iekšējās, gan ārējās.

Bieži izmanto betona krāsošanai, bet uzklājama arī uz citām virsmām. Piemērota kāpnēm, pagrabiem, balkoniem, izmantošanai mājsaimniecībās, sabiedriskās telpās uz virsmām, kas pakļautas vieglām, mehāniskām slodzēm.

Krāsa ir ūdens tvaiku caurlaidīga un krāsu toņu noturīga.

Piemērota lietošanai iekšdarbos un ārējās. (Piezīme: koka virsmām tikai iekšējās, neapstrādātām koka virsmām mēs iesakām izmantot Hagmans Spärrgrund). Krāsu uz jaunas cementa virsmas var uzklāt pēc 1 nedēļas. Lai palielinātu nodilumu pret skrāpējumiem un sniegtu vēl labāku izturību, virsmu iesakām pārklot ar Klarlack 1K. Telpām, kurās virsmas tiek pakļautas ķīmikāliju iedarbībai, mēs iesakām izmantot Hagmans Golfvärg EP-V.

TEHNISKĀ INFORMĀCIJA:

Saistviela: Poliuretāns / akrilāts
Materiāla patēriņš: Aptuveni 10m²/ 1l (1kārtā)
Difūzijas caurlaidība: Pie 2 kārtām, katra 0.1 l/m²

Cietēšanas laiks: Nogaidīt vismaz 3h pirms nākamās kārtas uzklāšanas. Grīdu drīkst izmantot pēc 12 stundām. Pilnībā nožuvusi pēc 5 - 7 dienām

Spīdums: 40 / pusspīdīgs
Sausais atlikums: Aptuveni 47 % no svara
Ugunsbīstamība: Nav uguns bīstams
Derīguma termiņš: 2 gadi, sargāt no sala

SAGATAVOŠANA:

Jaunām betona grīdām pirms apstrādes, jācietē vismaz 1 nedēļa, kā arī tām jābūt sausām un brīvām no netīrumiem, eļļām un līdzīga tipa netīrumiem. Cementa virskārtu ieteicams noslīpēt matētu vai lietot skābes saturošu mazgāšanas līdzekli.

Neapstrādātai koksnei zaru vietas jāapstrādā ar zaru laku un pēc tam virsma jānogruntē ar koksnes gruntējumu, lai mazinātu iekrāsošanās iespējas koka sveķu iedarbības rezultātā (tas īpaši attiecas uz tām koka virsmām, kuras ir plānots krāsot ar baltu vai gaišu krāsu). Ja produkts tiek klāts uz jau esošas krāsas kārtas, tad virsmai jābūt matētai un nolobījusies krāsa jānoņem.

UZKLĀŠANA:

Krāsu uzklāt ar otu vai rullīti. Nepieciešams uzklāt 2 kārtās. Krāsojot īpaši uzsūcošu pamatni, krāsu atšķaida ar 20% ūdens. Nodrošiniet labu ventilāciju. Ja mitrums pārsniedz 85%, virsma var palikt matēta un svītraina. Darbarīku tīrīšanai izmantojiet ūdeni. Zemākā virsmas temperatūra ir + 5°C.

Iepakojums:

1L, 4L, 10L

Krāsas:

Skatiet pieejamo krāsu klāstu, produktu datu lapās.



CE	
Hagmans Kemi AB Box 112 51110 Fritsla	
13	
EN 1504-2	
39511-002	
Produkts betona virsmu aizsardzībai Pārklājums	
Uguns klasifikācija	Br-s1
Ūdens tvaiku caurlaidība	Class I
Kapilārā absorbcija un ūdenscaurlaidība	w < 0,1 kg/m ² h ^{0,5}
Adhēzijas izturība	>2,0 N/mm ²

Floor Paint 1K

Hagmans Floor Paint 1K is easy-to-work-with, durable diffusion paint with good light and gloss durability. Hagmans Floor Paint 1K is a water-borne paint based on polyurethane/acrylate. NOTE: wood foundations; indoor use only! The paint is primarily intended for indoor and outdoor painting of floor and wall cement surfaces. It may also be used indoors on wood or fibreboards. The product is suitable for home use, as well as surfaces exposed to lighter trade traffic. Since the paint has good diffusion properties, it is suitable for painting on ground floors. For improved dirt resistance use Clear Lacquer 1K. For premises exposed to chemical handling, we recommend Hagmans Golvfärg EP-V.

Technical data

Base: Polyurethane/acrylate
 Diffusion-characteristics: Permeable to water vapour at 2 coats, each 0.1 l/m²
 Specific gravity: 1.2
 Curing time: Allow approx. 3 hours curing time before next coat.
 The floor may be brought into use after 12 hours. Full swear strength 5–7 days
 Lowest surface temperature: + 5°C
 Gloss value: Approx. 40 (half gloss)
 Fire hazard: No fire hazard
 Material-consumption: 1litre covers approx. 10m²/ coat.
 Shelf life: 2 year. Store protected from frost.
 Dry content: Approx. 47 % by weight

Preparation: New cement surfaces must have hardened for at least 1 week and be dry and free from dirt, oil and similar. The cement film must be removed by grinding, sandblasting or using an acid wash. mend Hagmans Floor Paint EP-V. Untreated wooden, the knots should be treated with knot lacquer and then surfaces should be primed with wood/joinery primer to reduce the risk of staining from wood resins (this applies especially to wooden surfaces to be painted in white or light colours). When covering an existing paint, the


surface must be ground matt and all loose paint removed.

Application: With a paintbrush or roller. Should be applied in two layers. When priming absorptive foundations, dilute the paint with 20 % water. Check for good ventilation. For humidity exceeding 85 % a matt and streaked surface may occur. Paintbrushes and other equipment are cleaned in water. Lowest surface temperature is +5°C.

Packaging: 1 L, 4 L, 10 L.

Colours: See colour chart. For further information check the data sheet of the product.



	
Hagmans Kemi AB Box 112 51110 Fritsla	
13	
EN 1504-2	
39511-002	
Product for the protection of concrete surfaces Coating	
Fire classification Permeability to water vapour Capillary absorption and permeability to water Adhesion strength	B _H -s1 Class I w < 0,1 kg/m ² h ^{0,5} >2,0 N/mm ²